

## TECHNICAL REPORT

<b>FABRIC:</b>		71100
<b>APPLICATION:</b>		Fashion Clothing
<b>FABRIC DETAIL</b>		
<b>Composition:</b>		100 % Cotton
<b>Texture:</b>		Denim 3x1
<b>Weight(OZ):</b>		11
<b>Weight(GSM):</b>		383
<b>Threads:</b>		Warp Ne 9 Weft Ne 9
<b>Density:</b>		Warp 81 Weft 46
<b>Width:</b>		159 cm
<b>Colour:</b>		Indigo
<b>PHYSICAL CHANGE</b>		
		<b>Results</b>
Breaking strength:	Warp	68 KG
	Weft	39 KG
Tear Resistance:	Warp	4523 GM
	Weft	2699 GM
Dimensional change in domestic washing and drying:	Warp	-2,00%
	Weft	-3,00%
<b>COLOUR FASTNESS</b>		
		<b>Results</b>
Colour fastness to rubbing:	Dry	4
	Wet	1-2
PH		7,5
The characteristics may vary within the commercial tolerances		
Washing conditions		